

180

**DE SOLUTII
PENTRU UN ZID**

NZEB





Densitate - $140 \pm 10 \text{ Kg/m}^3$
 λ dry element - $0,05 \text{ W/mK}$



Densitate - $300 \pm 25 \text{ Kg/m}^3$
 λ dry element - $0,08 \text{ W/mK}$



 izomineral	 megaterm		
Grosime (mm) Termoizolație	Grosime (mm) BCA	Grosime (mm) ZID	R (m ² K/W)
FĂRĂ TERMOIZOLATIE	350	350	4.05
	375	375	4.33
	400	400	4.61
50	250	300	4.01
50	300	350	4.57
50	350	400	5.12
50	375	425	5.4
50	400	450	5.68
75	250	325	4.47
75	300	375	5.03
75	350	425	5.58
75	375	450	5.86
75	400	475	6.14
100	200	300	4.37
100	250	350	4.92
100	300	400	5.48
100	350	450	6.03
100	375	475	6.31
100	400	500	6.59
125	200	325	4.83
125	250	375	5.38
125	300	425	5.94
125	350	475	6.49
125	375	500	6.77
125	400	525	7.05
150	200	350	5.28
150	250	400	5.83
150	300	450	6.39
150	350	500	6.94
150	375	525	7.22
150	400	550	7.5
175	200	375	5.74
175	250	425	6.29
175	300	475	6.85
175	350	350	7.4
175	375	550	7.68
175	400	575	7.96
200	200	400	6.19
200	250	450	6.74
200	300	500	7.3
200	350	550	7.85
200	375	575	8.13
200	400	600	8.41

Densitate - $140 \pm 10 \text{ Kg/m}^3$
 λ dry element - $0,05 \text{ W/mK}$



Densitate - $300 \pm 30 \text{ Kg/m}^3$
 λ dry element - $0,09 \text{ W/mK}$



 izomineral

 megaterm^{plus}



Grosime (mm) Termoizolație	Grosime (mm) BCA	Grosime (mm) ZID	R (m ² K/W)
FĂRĂ TERMOIZOLATIE	400	400	4.16
50	300	350	4.23
50	350	400	4.73
50	375	425	4.98
50	400	450	5.23
75	250	325	4.19
75	300	375	4.69
75	350	425	5.19
75	375	450	5.44
75	400	475	5.69
100	200	300	4.14
100	250	350	4.64
100	300	400	5.14
100	350	450	5.64
100	375	475	5.89
100	400	500	6.14
125	200	325	4.6
125	250	375	5.1
125	300	425	5.6
125	350	475	6.1
125	375	500	6.35
125	400	525	6.6
150	200	350	5.05
150	250	400	5.55
150	300	450	6.05
150	350	500	6.55
150	375	525	6.8
150	400	550	7.05
175	200	375	5.51
175	250	425	6.01
175	300	475	6.51
175	350	350	7.01
175	375	550	7.26
175	400	575	7.51
200	200	400	5.96
200	250	450	6.46
200	300	500	6.96
200	350	550	7.46
200	375	575	7.71
200	400	600	7.96

Densitate - $140 \pm 10 \text{ Kg/m}^3$
 λ dry element - $0,05 \text{ W/mK}$



Densitate - $400 \pm 30 \text{ Kg/m}^3$
 λ dry element - $0,10 \text{ W/mK}$





 izomineral	 standard	Grosime (mm) ZID	R (m ² K/W)
Grosime (mm) Termoizolație	Grosime (mm) BCA	Grosime (mm) ZID	R (m ² K/W)
50	350	400	4.28
50	375	425	4.49
50	400	450	4.71
75	300	375	4.3
75	350	425	4.74
75	375	450	4.95
75	400	475	5.17
100	250	350	4.32
100	300	400	4.75
100	350	450	5.19
100	375	475	5.4
100	400	500	5.62
125	200	325	4.34
125	250	375	4.78
125	300	425	5.21
125	350	475	5.65
125	375	500	5.86
125	400	525	6.08
150	200	350	4.79
150	250	400	5.23
150	300	450	5.66
150	350	500	6.1
150	375	525	6.31
150	400	550	6.53
175	200	375	5.25
175	250	425	5.69
175	300	475	6.12
175	350	350	6.56
175	375	550	6.77
175	400	575	6.99
200	200	400	5.7
200	250	450	6.14
200	300	500	6.57
200	350	550	7.01
200	375	575	7.22
200	400	600	7.44

Densitate - $140 \pm 10 \text{ Kg/m}^3$
 λ dry element - $0,05 \text{ W/mK}$



Densitate - $480 \pm 30 \text{ Kg/m}^3$
 λ dry element - $0,12 \text{ W/mK}$





 izomineral	 superblock		
Grosime (mm) Termoizolație	Grosime (mm) BCA	Grosime (mm) ZID	R (m ² K/W)
50	400	450	4.09
75	350	425	4.19
75	375	450	4.37
75	400	475	4.55
100	300	400	4.29
100	350	450	4.64
100	375	475	4.82
100	400	500	5.00
125	200	325	4.03
125	250	375	4.39
125	300	425	4.75
125	350	475	5.1
125	375	500	5.28
125	400	525	5.46
150	200	350	4.48
150	250	400	4.84
150	300	450	5.2
150	350	500	5.55
150	375	525	5.73
150	400	550	5.91
175	200	375	4.94
175	250	425	5.3
175	300	475	5.66
175	350	350	6.01
175	375	550	6.19
175	400	575	6.37
200	200	400	5.39
200	250	450	5.75
200	300	500	6.11
200	350	550	6.46
200	375	575	6.64
200	400	600	6.82

Densitate - $140 \pm 10 \text{ Kg/m}^3$
 λ dry element - $0,05 \text{ W/mK}$



Densitate - $550 \pm 50 \text{ Kg/m}^3$
 λ dry element - $0,14 \text{ W/mK}$



 izomineral	 structoterm	Grosime (mm) ZID	R (m ² K/W)
Grosime (mm) Termoizolație	Grosime (mm) BCA		
75	375	450	4.04
75	400	475	4.19
100	300	400	4.02
100	350	450	4.33
100	375	475	4.49
100	400	500	4.64
125	250	375	4.17
125	300	425	4.48
125	350	475	4.79
125	375	500	4.95
125	400	525	5.1
150	200	350	4.3
150	250	400	4.62
150	300	450	4.93
150	350	500	5.24
150	375	525	5.4
150	400	550	5.55
175	200	375	4.76
175	250	425	5.08
175	300	475	5.39
175	350	350	5.7
175	375	550	5.86
175	400	575	6.01
200	200	400	5.21
200	250	450	5.53
200	300	500	5.84
200	350	550	6.15
200	375	575	6.31
200	400	600	6.46

ODI CELCO

FII PRETENȚIOS! ALEGE-L PE CEL MAI BUN.

WWW.CELCO.RO

WWW.IZOMINERAL.RO